



PROPERTIES	TEST METHOD	POWER SCRIM FR6	POWER SCRIM FR10
APEARANCE		TRANSLUCENT CREAM COLOR	
THICKNESS, NOMINAL		6 MIL	10 MIL
WEIGHT		22 LBS / MSF	42 LBS / MSF
CONSTRUCTION		EXTRUSION LAMINATED SCRIM REINFORCEMENT	EXTRUSION LAMINATED SCRIM REINFORCEMENT
TENSILE STRENGTH	ASTM D822-00	YIELD STRESS (PSI) 1604 M / 648 T ELONGATION (%) 19.9 M / 38.3 T	YIELD STRESS (PSI) 1833 M / 628 T ELONGATION (%) 19.6 M / 58.5 T
GRAB TENSILE	ASTM D5034	PEAK LOAD (LBF) 51 M / 28 T ELONGATION (%) 1.2 M / 7.5 T	PEAK LOAD (LBF) 109 M / 48 T ELONGATION (%) 1.1 M / 16.3 T
TRAPEZOID TEAR	ASTM D751	PEAK LOAD (LBF) 70 M / 14 T ELONGATION (%) 176.6 M / 401.4 T	PEAK LOAD (LBF) 124 M / 24 T ELONGATION (%) 209.7 M / 251.4 T
MULLEN BURST	ASTM 751	130 (LBS/IN₂)	222 (LBS/IN₂)
MAXIMUM USE TEMP. MINIMUM USE TEMP.		180 F -70 F	180 F -70 F
BURNING CHARACTERISTICS FLAME SPREAD INDEX SMOKE DEVELOPED VALUE	ASTM E84-95 THIS TEST ALSO PUBLISHED UNDER: ANSI 2.5 NFPA 255 UBC 8-1 (42-1) UL 723	0 45	0 45

N.B.: THESE ARE TYPICAL PROPERTIES AND ARE INTENDED AS A GENERAL GUIDE ONLY, NOT AS SPECIFICATION LIMITS. NO WARRANTIES ARE EXPRESSED REGARDING FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO. NO GUARANTEE OF SATISFACTORY RESULTS FROM RELIANCE UPON CONTAINED INFORMATION. WE DISCLAIM ALL LIABILITY FOR RESULTING LOSS OR DAMAGE.

MIDWEST CANVAS CORP
4635 WEST LAKE ST.
CHICAGO, IL. 60644 773 287 4400